

	Type	Hits	Search Text	DBs
72	BRS	1053	349/122	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
73	BRS	108	428/1.5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
74	BRS	20917	anti-cracking or anticracking or antistress or anti-stress or (stress near (prevent\$4 or eliminat\$4))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
75	BRS	121370 8	adhesive or (bonding near agent)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
76	BRS	675	S86 same S87	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
77	BRS	135856 4	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
78	BRS	135856 4	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
79	BRS	182727 1	protecti\$5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
80	BRS	37844	S101 same S102	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
81	BRS	212083	\$5isocyanate or polyisocyanate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
82	BRS	7655	S104 same S102	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
83	BRS	366	S103 and S105	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
84	BRS	6614	S101 same S104	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
85	BRS	7332	S104 same (hardness or microhardness)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
86	BRS	1172	S110 same layer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
87	BRS	0	S111 same gpascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
88	BRS	1	S111 same pascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
89	BRS	21	S111 same pa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
90	BRS	25159	S102 same (urethane or polyurethane)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
91	BRS	1501	S122 and S101 and S104	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
92	BRS	182727 1	protecti\$5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
93	BRS	212083	\$5isocyanate or polyisocyanate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
94	BRS	7655	S128 same S127	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
95	BRS	1467	S129 same (glue or adhesive or binder)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
96	BRS	703	S130 same layer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
97	BRS	280	S130 and optical	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
98	BRS	2474	(lcd or (liquid near crystal near display)) same (el or electrolumin\$8) same (pd or plasma) same (fed or (field near emission))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
99	BRS	423	S138 and S139	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
100	BRS	1	10/502296	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
101	BRS	1	S111 same gigapascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
102	BRS	1	10/502296	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
103	BRS	5	"6814914"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
104	BRS	6	"5793020"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
105	BRS	19	"5193020"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
106	BRS	25	"5518783"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
107	BRS	19	"644439"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
108	BRS	2	"9418583"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
109	BRS	29	S80 and S81	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
110	BRS	12	S84 and S81	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
111	BRS	2	"6900937"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
136	BRS	333	(hardness or microhardness) near gpa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
137	BRS	364	S140 not S141	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
138	BRS	416	349/118	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
139	BRS	453	S123 and optical	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
140	BRS	522	positive near birefringence	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
141	BRS	564	S88 not S90	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
142	BRS	135856 4	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
143	BRS	97576	S89 and (S104 or epox\$3 or polyimide)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
144	BRS	2239	S138 same cholesterol\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
145	BRS	773	S144 and S145	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
146	BRS	162072	(adhesive or bonding or glue) same (S104 or epox\$3 or polyimide)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
147	BRS	189	S146 and S147	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
148	BRS	189	S145 and S147	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
149	BRS	50	S145 same (S104 or epox\$3 or polyimide)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
150	BRS	14	S150 and S147	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT